


PRIME HDPE DUCT (or 'sub-duct')



1 GENERAL

1.1 This document defines single continuous duct made from high quality HDPE, according to paragraph

2.1. It features a bonded low friction dry liner, to enable easy placement of fibre optic and power cables of suitable OD.

1.2 HDPE duct is supplied in coils or on returnable drums (wood or metal)

1.3 The finished product shall be free from cracks, holes, foreign inclusions or other defects that would

impair its performance. It shall be smooth walled inside and out and conform to the requirements of this document. A ribbed internal surface is available on request.

1.4 The finished product shall be capped ensuring the ends are watertight to prevent the ingress of contamination or foreign bodies likely to cause problems when cabling.

1.5 Duct is available with a standard 8kN pull-rope pre-installed. This may be called 'rope-in-duct'.

2 RAW MATERIALS

2.1 The tensile strength of the polyethylene stated by the supplier shall be no less than 23MPa.

2.2 The derived density of the polyethylene shall be not less than 0.95 g/ml when determined in accordance with Appendix B of BS 3412 Method B5.

2.3 The melt flow rate of the polyethylene compound shall be less than 0.4g/600s when measured in accordance with ISO 1133:2000.

2.4 The polyethylene shall be uniform in colour and free from foreign matter.

2.5 Both the polyethylene compound and the dry lubricant shall be protected against thermal degradation such that adequate stabilisation is imparted during processing of the material.

2.6 The polyethylene compound shall be adequately protected against ultraviolet degradation in accordance with ISO 877: Method 550B, normal daylight. Performance is based on maximum 6 months storage outdoors.

3 DIMENSIONS

3.1 The duct shall have dimensions (mm) as per the table below.

3.2 Ovality is the amount the greatest diameter exceeds the diameter at 90° to it, (at one position) divided by the average diameter. It is expressed as a percentage.

a) On the extrusion line (before the drumming/coiling operation): The ovality shall not exceed 3% (ducts up to OD 40mm). For ducts over nominal 40mm, the ovality shall not exceed 5%.

b) Coming off the drum or coil: The ovality shall not exceed 7% (ducts up to OD 40mm). For ducts over nominal 40mm, the ovality shall not exceed 10%.

3.3 The weight (mass) of the duct shall be nominally as stated in the table.

This document is intended as a guide only. Whilst the information it contains is believed to be correct, Emtelle can take no responsibility for actions taken based on the information contained in this document. Emtelle reserves the right to make changes to this document without notice. All sales of product are subject to Emtelle's terms and conditions of sale only, which can be found on Emtelle's website.

This document is protected by copyright (c) Emtelle UK Limited [2015]. The products depicted are protected by intellectual property rights. Any unauthorized copying of this document or of our products is prohibited and Emtelle UK Limited will take action to prevent any infringement of its rights and to claim damages for the loss that it suffers.

www.emtelle.com

'SIZE' OD/ID	SDR	MEAN OUTSIDE DIAM			I.D. nom	WALL THICKNESS			MASS nom g/m	max install tension	
		min	NOM	max		min	NOM	max		kN	kg
18 / 14	9.0	17.7	18	18.3	14	1.7	2.0	2.3	96	0.9	90
20 / 14	6.7	19.7	20	20.3	14	2.7	3.0	3.3	153	1.4	140
20 / 16	10.0	19.7	20	20.3	16	1.7	2.0	2.3	111	1.1	110
25 / 20	10.0	24.7	25	25.3	20	2.2	2.5	2.8	170	1.7	170
25 / 21	12.5	24.7	25	25.3	21	1.7	2.0	2.3	140	1.4	140
28 / 24	14.0	27.7	28	28.3	24	1.7	2.0	2.3	162	1.6	160
31 / 25	10.3	30.7	31	31.3	25	2.7	3.0	3.3	255	2.6	260
32 / 26	10.7	31.7	32	32.3	26	2.7	3.0	3.3	255	2.6	260
32 / 27	12.8	31.7	32	32.3	27	2.2	2.5	2.8	221	2.2	220
32 / 28	16.0	31.7	32	32.3	28	1.7	2.0	2.3	179	1.8	180
34 / 28	11.3	33.7	34	34.3	28	2.7	3.0	3.3	272	2.7	270
35 / 28	10.0	34.7	35	35.3	28	3.2	3.5	3.8	332	3.3	330
35 / 30	14.0	34.7	35	35.3	30	2.2	2.5	2.8	247	2.5	250
37 / 29	9.3	36.7	37	37.3	29	3.7	4.0	4.3	395	3.3	330
37 / 31	12.3	36.7	37	37.3	31	2.7	3.0	3.3	304	3	300
37 / 32	14.8	36.7	37	37.3	32	2.2	2.5	2.8	255	2.5	250
37 / 33	18.5	36.7	37	37.3	33	1.7	2.0	2.3	209	2	200
38 / 32	12.7	37.7	38	38.3	32	2.7	3.0	3.3	323	3.2	320
40 / 32	10.0	39.7	40	40.3	32	3.7	4.0	4.3	425	4.3	430
40 / 33	11.4	39.7	40	40.3	33	3.2	3.5	3.8	383	3.7	370
40 / 34	13.3	39.7	40	40.3	34	2.7	3.0	3.3	332	3.3	330
40 / 35	16.0	39.7	40	40.3	35	2.2	2.5	2.8	280	2.7	270
44 / 38	14.7	43.7	44	44.3	38	2.7	3.0	3.3	366	3.7	370
'50 / 41'	10.9	49.5	50	50.5	40.8	4.3	4.6	4.9	612	6.1	610
'50 / 42'	13.5	49.5	50	50.5	42.6	3.4	3.7	4.0	544	5.4	540
50 / 43	14.3	49.5	50	50.5	43	3.2	3.5	3.8	486	4.8	480
63 / 50	9.7	62.7	63	63.3	50	6.2	6.5	6.8	1105	11	1100
63 / 52	11.5	62.7	63	63.3	52	5.2	5.5	5.8	948	8.9	890

↳ 'SDR' is the standard dimension ratio (OD / wall). Lower SDRs indicate heavy-duty

sizes.

4 PERFORMANCE

4.1 TENSILE: The duct shall withstand the stated axial load when applied at 100mm/min to a 500mm gauge length. The elongation due to this load shall not exceed 5%.

NB: The expected tensile 'yield' load causes total failure of the duct. 'Yield' load is not a safe working load. At this load, the duct has normally elongated by around 10%, and then continues to elongate to failure.

4.2 a) INSTALLATION of DUCT: We recommend that installation tension does not exceed that specified in the previous table, and that correct installation procedures are followed. Pulling duct causes temporary elongation, which reduces when unloaded. After pulling and before cutting or connecting the duct, allow suitable relaxation time, ideally 24 hours or more.

b) INSTALLATION of Cable into DUCT: Use emtelle recommended methods. Do not exceed blow pressure listed below, or the duct may suffer deformation.

4.3 STIFFNESS of each duct at 5% deflection shall exceed that stated below. (Test to ASTM 2412, sample length 150mm)

4.4 COMPRESSION: The load expected to give 15% deflection on a 200mm length is given. (to EN 50086-2-4: sample length 200mm)

This document is intended as a guide only. Whilst the information it contains is believed to be correct, Emtelle can take no responsibility for actions taken based on the information contained in this document. Emtelle reserves the right to make changes to this document without notice. All sales of product are subject to Emtelle's terms and conditions of sale only, which can be found on Emtelle's website.

This document is protected by copyright (c) Emtelle UK Limited [2015]. The products depicted are protected by intellectual property rights. Any unauthorized copying of this document or of our products is prohibited and Emtelle UK Limited will take action to prevent any infringement of its rights and to claim damages for the loss that it suffers.

www.emtelle.com

- 4.5 IMPACT: All duct shall withstand (ie no cracks) a 15J impact at -5°C when tested to EN 50086-2-4. Test 12 samples. Sample length is 200mm
- 4.6 COIL SET: When 50m of duct is laid out and allowed to relax, the central part, excluding ends, shall lie substantially straight.
- 4.7 FRICTION: The frictional force (horizontal) on a standard pull-rope shall be no greater than 390N when lifting a 25kg mass (vertical) at a speed of 0.5m/min. The duct sample containing the rope shall be 5m long, and include a 450° loop of diameter 0.75m.
- 4.8 BENDING: Minimum recommended bend radius is as stated. If temp is below 5°C, MBR is greater, as stated. Do not go tighter than the MBR. Remember that the **greater** the installed bend radius, the less stress will be induced in the duct, and the easier that cables will blow or pull around the curve.
 **Barrel diameters for supply may be slightly tighter than this.

OD / ID	4.1 tensile test load (N)	4.1 expected tensile yield load (N) #	4.2 max recommend blow pressure bar	4.3 min stiffness ASTM 2412 kPa	4.4 expected load at 15% compression on 200mm length		4.8 Min bend radius** for handling and lifetime configuration	
					Newtons	kg	over 5°C	under 5°C
18 / 14	1100	2300	15				0.18m	0.24m
20 / 14	1700	3600	15				0.15m	0.21m
20 / 16	1300	2600	15				0.22m	0.3m
25 / 20	2000	4060	15	3000	1900	190	0.3m	0.4m
25 / 21	1650	3300	13		950	95	0.35m	0.5m
28 / 24	1900	3750	12				0.45m	0.65m
31 / 25	3000	6070	15	2500	1800	180	0.35m	0.5m
32 / 26	3000	6280	15	2100	1600	160	0.4m	0.55m
32 / 27	2600	5320	13	1500	1200	120	0.45m	0.65m
32 / 28	2100	4330	10	900	800	80	0.55m	0.75m
34 / 28	3200	6720	14	2000	1600	160	0.45m	0.55m
35 / 28	3900	7960	15	2500	2500	250	0.4m	0.55m
35 / 30	2900	5870	11				0.55m	0.80m
37 / 29	4000	9530	15				0.4m	0.55m
37 / 31	3600	7200	13				0.5m	0.7m
37 / 32	3000	6230	11	1000	1000	100	0.6m	0.85m
37 / 33	2400	5000	8				0.7m	1.0m
38 / 32	3800	7500	13				0.53m	0.75m
40 / 32	5000	10400	15	2800	2800	280	0.45m	0.65m
40 / 33	4500	9230	14	1800	1700	170	0.5m	0.7m
40 / 34	3900	8000	12				0.56m	0.8m
40 / 35	3200	6700	10				0.7m	1.0m
44 / 38	4300	8800	11				0.7m	1.0m
50 / 41	7200	14790	15	2200	2800	280	0.55m	0.8m
50 / 42	6400	13290	13	1200	1600	160	0.75m	1.05m
50 / 43	6000	11700	11				0.75m	1.05m
63 / 50	13000	26500	15				0.7m	1.0m
63 / 52	10900	22800	11				0.8m	1.1m

NOTE: Emtelle can supply additional sizes. Please enquire.

- 4.9 MARKING: Unless otherwise requested, the duct shall be marked as below at one metre intervals:
 <<Incremental metre-mark>><<Manufacturer's product code>><<Production date>><<Size of duct>><<Customer name and / or other special designations>><<
 (Colours and / or stripes are also available on request)

This document is intended as a guide only. Whilst the information it contains is believed to be correct, Emtelle can take no responsibility for actions taken based on the information contained in this document. Emtelle reserves the right to make changes to this document without notice. All sales of product are subject to Emtelle's terms and conditions of sale only, which can be found on Emtelle's website.
 This document is protected by copyright (c) Emtelle UK Limited [2015]. The products depicted are protected by intellectual property rights. Any unauthorized copying of this document or of our products is prohibited and Emtelle UK Limited will take action to prevent any infringement of its rights and to claim damages for the loss that it suffers.